

# WORLD WIDE ALLOYS

## TECHNICAL BULLETIN

### WearX® 200

Trade Name or Trademark: WearX® 200

Diameter Wire: 1/16" twin wired arc, cored spooled

Classification: none Applications: Abrasion resistance, Slip wear

Chemistry: nominal composition

Carbon	1.08 – 1.15
Chromium	15.5 – 17.0
Nickel	1.75 – 1.90
Manganese	1.45 – 1.62
Molybdenum	0.37 – 0.45
Boron	1.32 – 1.50
Silicon	(less than 1%)
Iron	balance

Comparative Wear Testing - Thermal Spray

7Nov2003

